Technical Data Sheet

Product	**LBA38**					
Description	Clear polyurethane sealer					
Color	Clear					
Woods / Substrates for which the product is suitable	Resinous softwood					
	Non resinous Softwood					
	Light color hardwood					
	Dark color hardwood					
	Exotic wood					
	Engineered woods, reconstituted woods, fine line					
Chemical-physical Properties	**Density (Kg/l)**	0,992	±	0,030		
	Density (lb/US gal)	8,3	±	0,3		
	Solid content %	48,3	±	2		
	Viscosity (EN ISO 2431) ISO 6 cup	26	±	2		
USAGE INDICATIONS						
Additional products		**Quantities**				
Hardener	LNB17	**In weight w/w %**			50	
		In volume v/v %			49,8	
	Solid content %	29,9	±	2		
Thinner	LZC1026	**In weight w/w %**			30	
		In volume v/v %			34	
READY TO USE PRODUCT PROPERTIES						
	Solid content 1st + 2nd component (%)	42,2	±	2		
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	2 h				
	Viscosity (Ford 4 cup)	18	±	2		
Application		**Quantities**				
	Airless spray	**gr/m² min-max:**	130	-	150	
		Wet Mils min-max	5,3	-	6,1	
	Airmix spray	**gr/m² min-max:**	130	-	150	
		Wet Mils min-max	5,3	-	6,1	
	Hand spray	**gr/m² min-max:**	130	-	150	
		Wet Mils min-max	5,3	-	6,1	

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3 - tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. € 10.000.000
codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157
milesi@ivmchemicals.com - www.milesi.com

PRODUCT PROPERTIES AFTER APPLICATION					
Drying					
	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	20 h			
	Dust free	15 min			
	Touch dry	30 min			
	Hard dry	20 h			
	Sandable after (time)	4 h			
	Overcoatability time	20 h			
	Overcoatability time between layers	1 h			
	Maximum time between layers without sanding	3 h			
	Hot air drying	(Time and temperature according to the drying system in use)			
Additional products		Quantities			
Properties	Good Elasticity				
Hardener	LNB42	In weight w/w %			50
		In volume v/v %			50,9
	Solid content %	26,5	±	2	
Thinner	LZC1026	In weight w/w %			30
		In volume v/v %			34
READY TO USE PRODUCT PROPERTIES					
	Solid content 1st + 2nd component (%)	41,0	±	2	
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	2 h			
	Viscosity (Ford 4 cup)	18	±	2	
Application		Quantities			
	Airless spray	gr/m² min-max:	130	-	150
		Wet Mils min-max	5,3	-	6,1
	Airmix spray	gr/m² min-max:	130	-	150
		Wet Mils min-max	5,3	-	6,1
	Hand spray	gr/m² min-max:	130	-	150
		Wet Mils min-max	5,3	-	6,1

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3 - tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. € 10.000.000
codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157
milesi@ivmchemicals.com - www.milesi.com

PRODUCT PROPERTIES AFTER APPLICATION					
Drying					
	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	20 h			
	Dust free	15 min			
	Touch dry	30 min			
	Hard dry	20 h			
	Sandable after (time)	4 h			
	Overcoatability time	20 h			
	Overcoatability time between layers	1 h			
	Maximum time between layers without sanding	3 h			
	Hot air drying	(Time and temperature according to the drying system in use)			
Additional products		Quantities			
Properties	Good Yellowing resistance				
Hardener	LNB20	In weight w/w %			50
		In volume v/v %			50,9
	Solid content %	25,0	±	2	
Thinner	LZC1026	In weight w/w %			30
		In volume v/v %			34
READY TO USE PRODUCT PROPERTIES					
	Solid content 1st + 2nd component (%)	40,5	±	2	
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	2 h			
	Viscosity (Ford 4 cup)	18	±	2	
Application		Quantities			
	Airless spray	gr/m² min-max:	130	-	150
		Wet Mils min-max	5,3	-	6,1
	Airmix spray	gr/m² min-max:	130	-	150
		Wet Mils min-max	5,3	-	6,1
	Hand spray	gr/m² min-max:	130	-	150
		Wet Mils min-max	5,3	-	6,1

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3
- tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. € 10.000.000
codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157
milesi@ivmchemicals.com - www.milesi.com

PRODUCT PROPERTIES AFTER APPLICATION		
Drying		
	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	20 h
	Dust free	15 min
	Touch dry	30 min
	Hard dry	20 h
	Sandable after (time)	4 h
	Overcoatability time	20 h
	Overcoatability time between layers	1 h
	Maximum time between layers without sanding	3 h
	Hot air drying	(Time and temperature according to the drying system in use)
Shelf life	18 months after production	
SPECIFIC WARNINGS	Being exotic woods of different source and variety, it is recommended to make preliminary tests to determine the coating cycle reliability	

WARNINGS

In a coating process with professional products:

- besides the product quality, the final result also depends on numerous other variables, such as environmental conditions; homogeneity in the quality of the support; the constancy of the application cycle; the plants performance; the proper use of the product, etc.
- in the process of industrial coating a certain waste of product is to be considered normal and therefore not attributable to product quality
- The final colour is influenced by the quality and preparation of the support and the conditions of application, for this reason it is essential to check in advance the result in terms of final use

Our Company cannot ensure the control of the coating process carried out by the user. We cannot, therefore, take on any responsibility for the final result achieved through the use of our products.
On the other hand, we guarantee the consistency of the chemical and physical characteristics of the product indicated in the relevant Technical Data Sheet, pledging to replace it if it does not correspond to the declared features
Data on the chemical and physical characteristics of the product are recorded at 20°C / 68°F and 70% R.U.

For best results, the optimum conditions of application are:

- Ambient temperature between 18 and 22°C (64 - 72 °F)
- ambient relative humidity between 65 and 70%
- support humidity between 8 and 14%

The conditions to be observed scrupulously are:

- A solvent-based product should be stored indoors at temperatures not below 0 °C / 32°F or above 35 °C / 95°F, in a properly ventilated place, not exposed to solar radiation
- Always shake the products well before use
- Before use, always shake well the product mixed with any other components such as catalysts, accelerators, thinners
- The application must not take place at a temperature lower than 15 °C / 59°F or above 30°C / 86°F
- The drying should not take place at a temperature below 15 °C / 59°F
- The ambient relative humidity during drying should be between 50% and 70%
- To decant paints, exclusively use containers made of suitable material, such as polyethylene and stainless steel
- After use, we recommend that you always close the can carefully

The end result of the coating cycle is the sole responsibility of the users, who must make sure that the product matches their needs and that environmental conditions, application or media specifications do not require substantial changes of use

It is the user's responsibility:

- Adhere to the conditions indicated above
- comply with the rules of hygiene and safety during product application, according to the descriptions given in the safety data sheets
- for solvent-based products spark-proof equipment should be used
- It is forbidden to smoke while using the product

At the bottom of each sheet there is a date of validity
The Company invites you to check with their staff that the product data sheet in your possession is the most updated, since the characteristics of the products are subject to adjustments over time
For more information, please contact (see below):

Issue date: 01/08/2017 **Rev.:** 4

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3
- tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. € 10.000.000
codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157
milesi@ivmchemicals.com - www.milesi.com