TECHNICAL DATA SHEET

Release: 7

Date: 27/11/2018

PRODUCT CODE: G950	**COMMERCIAL NAME:** VF A 913
DESCRIPTION: Two-components transparent polyurethanic sealer	

PROPERTIES	
Recommended for / Main area of application	Two-components polyurethanic transparent sealer with excellent covering properties, good sanding properties and good transparency. Suggested to paint furniture and accessories for interior, where a high coverage is required.
Application Method	By spraygun and by curtain coateer
Shelf life	24 months

APPLICATION PROPERTIES		PHISICAL PROPERTIES	
Quantity	150 - 180 gr/mq	**Viscosity**	62" +/- 6" DIN 4
Vertical Stability	-	**Solid Content**	50 +/- 3%
Cathalysis	B370 50%	**Specific Weight**	0,980 +/- 0,020 Kg/Lt
Dilution	P730 20 - 30%	**Glossy**	-
Pot Life	> 3 h	**Ph**	-

GENERAL INFORMATION			
Drying at 20°C		**Oven Drying**	
Dust Free	10'	**Time for Flash Off**	-
Touch Free	60'		
Sanding	8 h	**Time for drying**	-
Overcoating	-		
Stackable	12 h	**Time for cooling**	-

RECOMMENDED APPLICATION PROCESS
Apply a coat of a stain, suggested serie C520 - UNICOLOR SERIE. After 30 minutes apply by spraygun 150 - 180 gr/mq of G950 -VF A 913 catalysed at 50% with B370 - CAT. B 37 and thinned at 20 - 30% with P730 - DILUENTE POL. EXTRA. After 40 - 60 minutes apply a second coat of G950 - VF A 913, as above explained. After 12 hours sand with sand paper 220 - 400 and apply a coat of a polyurethanic matt topcoat, suggested serie H010 - VM 100 VARI GLOSS or H410 - VPK 744 VARI GLOSS.

ALTERNATIVE HARDENERS		PERFORMANCES
B400	50%	-
B540	50%	Higher covering properties
-	-	-

ALTERNATIVE THINNER
-

NOTES	User is responsible to make the application of the product in a place with an adequate air-recycle and on respecting of all hygienic and safety regulations.

Verinlegno S.p.A.
Via L. Galvani, 7
51010 - Massa e Cozzile (PT)

Tel. 0572. 92711
Fax 0572. 773608
info@verinlegno.it

Capitale Sociale int. Vers. Euro 1.020.000,00
Cod. Fisc./Part. IVA IT00230480477
R.E.A. PT N. 82948 - R.I. PT N. 00230480477

Responsible Care®
OUR COMMITMENT TO SUSTAINABILITY

STORAGE	Containers must be stored tightly closed in a well-ventilated place with temperatures between 5° C and 35°C.