TECHNICAL DATA SHEET

Release: 3

Date: 17/01/2019

PRODUCT CODE: M56020	**COMMERCIAL NAME:** CONVERTER ACRIL FO FI BIANCO 20 GLOSS
DESCRIPTION: Two-components acrylic white self sealer	

PROPERTIES	
Recommended for / Main area of application	Two-components acrylic white enamel with excellent quality, with high mechanical and chemical resistance. Excellent resistance to light, good covering properties, sanding properties and elasticity. Particularly suitable to paint wooden substrates with open pore. Suggested for furniture for interior in general, bathrooms, kitchens, wardrobes and doors.
Application Method	By spraygun
Shelf life	24 months

APPLICATION PROPERTIES		PHISICAL PROPERTIES	
Quantity	130 - 150 gr/mq	**Viscosity**	80" +/- 8" DIN 4
Vertical Stability	-	**Solid Content**	47 +/- 3%
Cathalysis	B420 20%	**Specific Weight**	1,100 +/- 0,020 Kg/Lt
Dilution	P730 30 - 50%	**Glossy**	20 +/- 3 G
Pot Life	10 h	**Ph**	-

GENERAL INFORMATION			
Drying at 20°C		**Oven Drying**	
Dust Free	20' - 30'	**Time for Flash Off**	-
Touch Free	90' - 120'		
Sanding	8 - 12 h	**Time for drying**	-
Overcoating	At least 8 - 12 h - up to 10 days without sanding with acrylic topcoat		
Stackable	12 h	**Time for cooling**	-

RECOMMENDED APPLICATION PROCESS
On an ash substrate, that has been opportunely sanded with sand paper 180 and brushed with a steel brush, apply by spraygun 130 - 150 gr/mq of M56020 - CONVERTER ACRIL FO FI BIANCO 20 GLOSS catalysed at 20% with B420 - CAT. B 42 and thinned at 30 - 50% with P730 - DILUENTE POL. EXTRA. After about 8 - 12 hours sand with sand paper 220, then with 320 - 400 and apply a second coat of M56020 - CONVERTER ACRIL FO FI BIANCO 20 GLOSS, as above explained.

ALTERNATIVE HARDENERS		PERFORMANCES
B410	30%	-
-	-	-
-	-	-

ALTERNATIVE THINNER
P030 30 - 50%

Verinlegno S.p.A.
Via L. Galvani, 7
51010 - Massa e Cozzile (PT)

Tel. 0572. 92711
Fax 0572. 773608
info@verinlegno.it

Capitale Sociale int. Vers. Euro 1.020.000,00
Cod. Fisc./Part. IVA IT00230480477
R.E.A. PT N. 82948 - R.I. PT N. 00230480477

Responsible Care®
OUR COMMITMENT TO SUSTAINABILITY

NOTES	User is responsible to make the application of the product in a place with an adequate air-recycle and on respecting of all hygienic and safety regulations.

STORAGE	Containers must be stored tightly closed in a well-ventilated place with temperatures between 5° C and 35°C.