TECHNICAL DATA SHEET

Release: 0

Date: 12/03/2021

PRODUCT CODE: D6103445E	**COMMERCIAL NAME:** PAT. IDRO N61 ORO 3445 E
DESCRIPTION: Water-based pigmented ageing patina	

PROPERTIES	
Recommended for / Main area of application	Water-based pigmented ageing patina, suitable on every kind of wood. Suggested for furniture, furnishing and objects.
Application Method	By spraygun
Shelf life	12 months

APPLICATION PROPERTIES		PHISICAL PROPERTIES	
Quantity	30 - 50 gr/mq	**Viscosity**	20" +/- 5" DIN 4
Vertical Stability	-	**Solid Content**	11 +/- 2%
Cathalysis	-	**Specific Weight**	1,020 +/- 0,020 Kg/Lt
Dilution	-	**Glossy**	-
Pot Life	Unlimited	**Ph**	-

GENERAL INFORMATION			
Drying at 20°C		**Oven Drying**	
Dust Free	10'	**Time for Flash Off**	-
Touch Free	20'		
Sanding	20' with steel wool	**Time for drying**	-
Overcoating	30'		
Stackable	-	**Time for cooling**	-

RECOMMENDED APPLICATION PROCESS
On a raw wooden substrate, that has been opportunely prepared, apply a coat of a polyurethanic sealer, suggested G340 - G350 - G360 - SOTTOSMALTO SERIE COLORATA. The following day apply by spraygun 30 - 50 gr/mq of D6103445E - PAT. IDRO N61 ORO 3445 E, ready for use. When it has dried sand with scotch brite or by steel sponge and apply a coat of an acrylic topcoat, suggested serie M150 - OBI 150 VARI GLOSS.

ALTERNATIVE HARDENERS		PERFORMANCES
-	-	-
-	-	-
-	-	-

ALTERNATIVE THINNER
-

NOTES	User is responsible to make the application of the product in a place with an adequate air-recycle and on respecting of all hygienic and safety regulations.

Verinlegno S.p.A.
Via L. Galvani, 7
51010 - Massa e Cozzile (PT)

Tel. 0572. 92711
Fax 0572. 773608
info@verinlegno.it

Capitale Sociale int. Vers. Euro 1.020.000,00
Cod. Fisc./Part. IVA IT00230480477
R.E.A. PT N. 82948 - R.I. PT N. 00230480477

Responsible Care®
OUR COMMITMENT TO SUSTAINABILITY

STORAGE	Don't keep product in a place with temperature < 5°C (it does not stand cold) and > 35°C. The drying of water-based products must take place in suitable and well ventilated places (temperature > 15°C and relative humidity < 85%).